

AMENDMENTS TO THE SPECIFICATION

IN THE SPECIFICATION:

Please replace the paragraph beginning on page 23, line 12, with the following rewritten paragraph:

The primer paint was applied on a support consisting of an aromatic polyamide film ("MICTRON" (trade name) of TORAY, Thickness: 3.9 μm , Young's modulus in machine direction (MD) = 11 GPa, Young's modulus in MD/Young's modulus in transverse direction (TD) = 0.70) in an amount such that the thickness after drying and calendering was ~~4.4 μm to~~ 1.0 μm for a primer layer. Then, on the formed primer layer, the above magnetic paint was applied in an amount such that the thickness after orientation in a magnetic field, drying and calendering was 0.2 μm , and orientated in a magnetic field and dried to form a magnetic layer.